PRODUCT DATA SHEET

Delta Glass PC 58





Description

PC 58 is a two part-component modified cold adhesive based on bitumen emulsion without solvents. PC 58 is used for applying Delta Glass insulation boards to concrete surfaces or as a surface coating on Delta Glass insulation prior to the application of a bitumen-based torch-on or self-adhesive membrane.

Fields of Application

- Adhesives for Delta Glass insulation
- Sealant for Delta Glass insulation

Packaging

PC 58 is supplied in a 32 kg container (net content) – consisting of 24 kg of emulsion and 8 kg of powder component.

Storage

- · Store cool and dry in a closed container
- Protect against heat and direct sunlight
- The adhesive must be protected from frost
- Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking
- Store only in original container
- \cdot Keep at temperatures between +5 and +30°C

Guarantees

Delta Membrane Systems Limited offer a 30-year Product Guarantee on Type C membranes, seals and fixings when a Delta Waterproofing System has been installed by a Delta Registered Installer. A list of experienced Delta Registered Installers is available from Delta's offices.

Product Details

DMS Special Order

Safety

Always follow the instructions provided in the material safety data sheet and take the precaution described there. Wear appropriate Protective Personal Equipment (PPE) when applying and using the material. Observe all governmental, state, and local safety regulations when processing the material.

- May cause allergic skin reaction
- Erythema (skin redness)
- Ingestion may cause gastro intestinal irritation, nausea, vomiting and diarrhoea.

Installations

Please refer to Delta's Installation Guides. Installation Guides can be found at www.deltamembranes.com/technical/deltainstallation-guides/. We have a number of "How to" subject related video guides available on your Youtube Channel and Website. Please visit www.deltamembranes.com/technicalcategories/the-video-suite

Associated Products

- Delta Glass Floor Board T4+
- Delta Glass Roof Board F2 T3+



PRODUCT DATA SHEET

Delta Glass PC 58

Technical Data

Delta Glass PC 58	
Туре	Two-component Adhesive, Hydraulically Setting
Basis	Component A: Bitumen Emulsion Component B: Calcium Silicates, Calcium Aluminate, Calcium Aluminate Ferrite
Consistency	Pasty
Service Temperature	-15°C to +45°C
Application Temperature (Air + Subsurface)	+5°C to +35°C (not on frozen substrates)
Application Time	At 20 °C: App. 90 Minutes
Surface Drying Time	Approx. 3 Hours
Depth Drying Time	1 to 3 Days
Mass Density	Approx. 1.20kg/dm³
Colour	Black/Brown
Water Vapour Diffusion Resistance.	μ= Approx. 25,000
Water Solubility	Insoluble After Complete Drying
Solvents	None
Reaction to Fire (EN 13501-1)	E
VOC	Free
Giscode	BBP 10

The physical properties indicated above are average values, which are measured under typical conditions. These values may be influenced by insufficient mixing, the type of laying, the layer thickness and the atmospheric conditions during and after application. In particular drying times are affected by temperature, air humidity, sun irradiation, wind, etc.

Additional information can be found in our Technical Data Sheets (TDS). Our liability and responsibility are guided exclusively by our general terms and conditions and are not expanded by the statement of our technical documents nor by the advice of our technical field service.

Other Information

All data and information contained in these Product/Technical Data Sheets is up-to-date and correct as at the date of issue. The information given is suggested as guidance and should only be used for evaluating your specific application. Delta Membrane Systems Limited cannot control or anticipate the conditions under which this product may be used, each user should review the information in specific context of the planned use. The information contained in these Product/Technical Data Sheets should not be considered a warranty, expressed, or implied, including but not limited to a warranty of merchantability or fitness for a particular purpose. In no event shall Delta Membrane Systems Limited be considered a liable for any incidental or consequential damages resulting from the use, misuse, or inability to use the product. This exclusion applies regardless of whether such damages are sought based on breach of warranty, breach of contract, negligence, strict liability in tort, or any other legal theory. When in doubt, contact Delta's Technical Team on 01992 523 523.